

## PATENT ABSTRACTS OF JAPAN

(11)Publication number : **07-305227**  
(43)Date of publication of application : **21.11.1995**

---

(51)Int.Cl.

**D01F 6/84**  
**C08L 67/00**  
**D01F 6/62**  
**// C08G 63/664**

---

(21)Application number : **06-117493**

(71)Applicant : **KANEBO LTD**  
**SHIMADZU CORP**

(22)Date of filing : **06.05.1994**

(72)Inventor : **KONDO YOSHIKAZU**  
**MATSUI MASAO**  
**KOSEKI HIDEKAZU**  
**FUJII YASUHIRO**

---

### **(54) METHOD FOR PRODUCING HIGHLY STRONG POLYLACTIC ACID FIBER**

#### **(57)Abstract:**

**PURPOSE:** To obtain highly strong polylactic acid fiber excellent in toughness, heat resistance and biodegradability and useful for clothing, medical treatments, etc., by continuously copolymerizing a specific amount of L-lactic acid, etc., with a specific amount of polyethylene glycol and subsequently spinning the copolymer under specific conditions.

**CONSTITUTION:** This method for producing the highly strong polylactic acid fiber comprises continuously copolymerizing 99.9–85wt.% of L-lactic acid, D-lactic acid and/or their cyclic dimers (lactides) with 0.1–15wt.% of a polyethylene glycol having a mol.wt. of  $\geq 300$  in a melted state, directly melt-spinning the melted copolymer in a spinning head without solidifying and pelletizing the copolymer, drawing the spun fiber to a length of  $\geq 3$  times, and subsequently thermally treating the drawn fiber. The obtained objective polylactic acid fiber maintains a mol.wt. of  $\geq 70000$  and has a fiber strength of  $\geq 3$ g/d. A hindered phenol compound and/or a hindered amine compound are preferably added to the polymerization system in amounts of  $\geq 10$ ppm, and the melting point of the fibers is preferably  $\geq 130^\circ$  C.